

Appln. No. 10/502,109

Attorney Docket No. 10555-46

I. Amendments to the Claims

1. (Currently amended) A photodiode comprising:
a semi-insulating substrate layer;
a first p-type semiconductor layer;
an n-type semiconductor layer; and
a second p-type semiconductor layer disposed between the first p-type semiconductor layer and the n-type semiconductor layer such that the second p-type semiconductor is directly adjacent to the n-type semiconductor, the second p-type semiconductor layer having a graded doping concentration along the path of the carriers.
2. (Original) The photodiode of claim 1 further comprising an anode layer for collecting holes.
3. (Original) The photodiode of claim 1 further comprising a cathode layer for collecting electrons.
4. (Original) The photodiode of claim 1 wherein the first p-type semiconductor layer is InAlAs.
5. (Original) The photodiode of claim 1 wherein the n-type semiconductor layer is InAlAs.
6. (Original) The photodiode of claim 1 wherein the second p-type semiconductor layer is InGaAs.
7. (Original) The photodiode of claim 1 wherein the graded doping concentration defines a first concentration adjacent to the first p-type semiconductor layer and a second concentration adjacent to the n-type

BRINKS
HOFFER
GILSON
LIONE

BRINKS HOFER GILSON & LIONE
PO Box 10395
Chicago, IL 60610

Appln. No. 10/502,109

Attorney Docket No. 10555-48

semiconductor layer, and further wherein the first concentration is greater than the second concentration.

8. (Previously Amended) A photodiode comprising:
 a first p-type semiconductor layer;
 an n-type semiconductor layer; and
 a second p-type semiconductor layer disposed between the first p-type semiconductor layer and the n-type semiconductor layer such that the second p-type semiconductor is directly adjacent to the n-type semiconductor, the second p-type semiconductor layer having a graded doping concentration, the graded doping concentration defining a first concentration adjacent to the first p-type semiconductor layer and a second concentration adjacent to the n-type semiconductor layer, the first concentration being greater than the second concentration, and
 the first concentration being located at a position x_0 and defining a concentration p_0 , and the graded doping concentration being governed by the following equation:

$$p = p_0 e^{\frac{-x}{D}}$$

over the depth D of the second p-type semiconductor layer for all x and D greater than zero.

9. (Previously Amended) The photodiode of claim 8 wherein the depth, D, for the first concentration is between 800 and 1000 angstroms in length.

10. (Previously Amended) A method of fabricating a photodiode comprising:
 providing a substrate layer;

BRINKS
 HOFER
 GILSON
 & LIONE

BRINKS HOFER GILSON & LIONE
 PO Box 10395
 Chicago, IL 60610

Appln. No. 10/502,109

Attorney Docket No. 10555-46

depositing an n-type semiconductor layer on the substrate;
depositing a second p-type semiconductor layer having a p-type dopant on the n-type semiconductor layer;
grading the p-type dopant of the second p-type semiconductor layer from a first concentration to a second concentration, the first concentration being greater than the second concentration; and
depositing a first p-type semiconductor layer on the second p-type semiconductor layer, the second p-type semiconductor layer being between the first p-type semiconductor layer and the n-type semiconductor layer such that the second concentration is directly adjacent to the n-type semiconductor layer.

11. (Original) The method of claim 10 further comprising the step of affixing an anode to collect holes.

12. (Original) The method of claim 10 further comprising the step of affixing a cathode to collect electrons.

13. (Original) The method of claim 10 wherein the first p-type semiconductor layer is InAlAs.

14. (Original) The method of claim 10 wherein the n-type semiconductor layer is InAlAs.

15. (Original) The method of claim 10 wherein the second p-type semiconductor layer is InGaAs.

16. (Previously Amended) A method of fabricating a photodiode comprising:

providing a substrate layer;
depositing an n-type semiconductor layer on the substrate;

BRINKS
HOFFER
GILSON
& LIONE

BRINKS HOFER GILSON & LIONE
PO Box 10395
Chicago, IL 60610

Appln. No. 10/502,109

Attorney Docket No. 10555-46

depositing a second p-type semiconductor layer having a p-type dopant on the n-type semiconductor layer;

grading the p-type dopant of the second p-type semiconductor layer from a first concentration to a second concentration, wherein the first concentration is greater than the second concentration; and

depositing a first p-type semiconductor layer on the second p-type semiconductor layer, wherein the second p-type semiconductor layer is between the first p-type semiconductor layer and the n-type semiconductor layer such that the second concentration is directly adjacent to the n-type semiconductor layer, and

wherein the first concentration is located at a position x_0 and defines a concentration p_0 , and further wherein the graded doping concentration is governed by the following equation:

$$p = p_0 e^{\frac{-x}{D}}$$

over the depth D of the second p-type semiconductor layer for all x and D greater than zero.

17. (Original) A photodiode having a first p-type semiconductor layer and an n-type semiconductor layer comprising:

a second p-type semiconductor layer disposed between the first p-type semiconductor layer and the n-type semiconductor layer such that the second p-type semiconductor is directly adjacent to the n-type semiconductor, the second p-type semiconductor layer having a graded doping concentration, wherein the graded doping concentration is governed by the following equation:

$$p = p_0 e^{\frac{-x}{D}}$$



BRINKS HOFER GILSON & LIONE
PO Box 10395
Chicago, IL 60610

Appin. No. 10/502,109

Attorney Docket No. 10555-46

over the depth D of the second p-type semiconductor layer for all x and D greater than zero.

18. (Original) The photodiode of claim 17 wherein the second p-type semiconductor layer is a type III-V semiconductor.

19. (Original) The photodiode of claim 17 wherein the second p-type semiconductor layer is InGaAs.

BRINKS
HOFFER
GILSON
& LIONE

BRINKS HOFER GILSON & LIONE
PO Box 10395
Chicago, IL 60610